

FABRICATION OF  $\text{Cu}_2\text{O}$  BASED HOMOSTRUCTURE THIN FILMS USING  
ELECTRODEPOSITION METHOD

NURLIYANA BINTI MOHAMAD ARIFIN

A thesis submitted in  
fulfillment of requirement for the award of the  
Degree of Master of Electrical Engineering



PTTAUTHM  
PERPUSTAKAAN TUNKU TUN AMINAH

Faculty of Electrical and Electronic Engineering  
Universiti Tun Hussein Onn Malaysia

MARCH 2018

## DEDICATION

*Every challenging work need self-efforts as well as guidance of elders especially those who very close to our hearts. My humble effort I dedicate to my dearest husband, Muhammad Sallehudin Bin Khalid, my beloved mother and father, Rahamah Binti Sumani and Mohamad Arifin Bin Sirat whose affection, love, encouragement and prays of days and nights make me able to complete this project.*

*Alhamdulillah. Thank you.*



PTTA UTHM  
PERPUSTAKAAN TUNKU TUN AMINAH

## ACKNOWLEDGMENT

In the name of Allah, the Most Gracious and the Most Merciful

Alhamdulillah, all praises to Allah for the strengths and His blessing in completing this thesis. I would like to express my gratitude and appreciation to all those who gave me the opportunity to complete this thesis. A special thanks to my project supervisor, Dr. Fariza Binti Mohamad, who gives a lot of guidance's during coordinating my project especially in experiment and maintains project's progress in track.

I would also like to acknowledge with much appreciation to the crucial of staff of Microelectronic and Nanotechnology Shamsuddin Research Centre (MiNT-SRC), who gave the permission to use all the required machinery and the necessary material to complete the project. Thanks also to lecturers as well as the panels especially in my project presentation that has improved my presentation skill by their comment and tips.

Last but not least, my deepest gratitude goes to all my friends for their kindness and moral support during my study. To those who indirectly contributed in this project, all of your kindness means a lot to me. Thank you very much.



## ABSTRACT

Copper oxide ( $\text{Cu}_2\text{O}$ ) is one of inorganic materials used in photovoltaic (PV) technology. It was reported that  $\text{Cu}_2\text{O}$  that acts as the p-n junction semiconductor material was preferable in extensive studies for solar cell application. However, the heterojunction interface between p-type  $\text{Cu}_2\text{O}$  to other materials has lower conversion efficiency due to lattice mismatch. Thus, a p-n  $\text{Cu}_2\text{O}$  homojunction thin film had been introduced to acquire higher efficiency due to similar interface which can promote less defects between layers. In this experiment, both n and p-type  $\text{Cu}_2\text{O}$  thin film was fabricated by using copper acetate based solution through electrodeposition method. Firstly, the effects of pH value and deposition time were optimized for fabrication of n-type  $\text{Cu}_2\text{O}$  thin film on fluorine doped thin oxide (FTO) glass. The deposition potential optimization was conducted using Cyclic Voltammetry Measurement. Then, the effects of bath temperature and deposition time were optimized for p-type  $\text{Cu}_2\text{O}$  on n-type  $\text{Cu}_2\text{O}$ /FTO substrate to obtain p-type based homostructure. Structural, morphological, topological and optical properties were characterized by using Cyclic Voltammetry, X-ray diffraction (XRD), Field Emission-Scanning Electron Microscope (FE-SEM), Atomic Force Microscopy (AFM) and Ultraviolet-Visible Absorption Spectroscopy (UV-Vis), respectively. The conduction type for n-type and p-type  $\text{Cu}_2\text{O}$  thin film also have been characterized by using Photoelectrochemical Measurement (PEC). The optimum parameters obtained for n-type  $\text{Cu}_2\text{O}$  were pH of 6.3, deposition time of 30 minutes, bath temperature of 60 °C and deposition potential of -0.125V vs Ag/AgCl. Meanwhile, the optimum parameters for fabrication of p-type  $\text{Cu}_2\text{O}$  on n-type  $\text{Cu}_2\text{O}$ /FTO substrate were pH of 12.5, deposition time of 2 hours, bath temperature of 40 °C and potential deposition of -0.4 V vs Ag/AgCl. The p-type  $\text{Cu}_2\text{O}$  based homostructure thin film was successfully fabricated and can be implemented in fabrication of  $\text{Cu}_2\text{O}$  homojunction thin film in photovoltaic for solar cell.

## ABSTRAK

Kuprum Oksida ( $\text{Cu}_2\text{O}$ ) adalah bahan bukan organik yang digunakan dalam teknologi fotovolt.  $\text{Cu}_2\text{O}$  yang bertindak menjadi bahan semikonduktor simpang p-n adalah lebih diutamakan dalam kajian aplikasi sel solar. Walaubagaimanapun, permukaan heterosimpang antara  $\text{Cu}_2\text{O}$  jenis p dengan bahan-bahan lain mempunyai kecekapan perubahan yang rendah berdasarkan tiada kesepadanan kekisi. Oleh itu, filem nipis  $\text{Cu}_2\text{O}$  jenis p-n homosimpang telah diperkenalkan untuk memperoleh kecekapan perubahan lebih tinggi berdasarkan permukaan sama yang mengurangkan kecacatan antara lapisan. Dalam kajian ini, kedua-dua  $\text{Cu}_2\text{O}$  jenis p dan n telah difabrikasi menggunakan campuran berasaskan kuprum asetat melalui teknik pengelektropendapan. Pertamanya, kesan nilai pH dan masa telah dioptimumkan untuk memfabrikasi filem nipis  $\text{Cu}_2\text{O}$  jenis n diatas kaca Fluorin Dop Stanum Oksida (FTO). Optimum potential ini telah dijalankan menggunakan pengukur voltammetri berkitar. Kemudian, kesan suhu dan masa dioptimumkan untuk filem nipis  $\text{Cu}_2\text{O}$  jenis p diatas filem nipis  $\text{Cu}_2\text{O}$ /FTO jenis n untuk membentuk homostruktur jenis p. Sifat struktur, morfologi, topologi dan optik filem nipis tersebut masing-masing telah dikenalpasti dengan menggunakan Belauan Sinar-X, Mikroskop Elektron Pengimbas Pancaran Medan (FE-SEM), Mikroskop Daya Atom (AFM) dan Spektrum Serapan Nampak Ultraviolet (UV-Vis). Jenis konduktor untuk filem nipis  $\text{Cu}_2\text{O}$  jenis n dan p juga telah dikenalpasti dengan menggunakan Pengukur Fotoelektrokimia (PEC). Parameter optimum yang didapati untuk filem nipis  $\text{Cu}_2\text{O}$ /FTO jenis n adalah nilai pH 6.3, masa selama 30 minit, suhu campuran  $60^\circ\text{C}$  dan potential  $-0.125\text{V}$  vs  $\text{Ag}/\text{AgCl}$ . Manakala, kajian juga mendapati parameter yang optimum untuk filem nipis  $\text{Cu}_2\text{O}$  jenis p diatas  $\text{Cu}_2\text{O}$ /FTO jenis n adalah nilai pH 12.5, masa pemendapan selama 2 jam, suhu campuran  $40^\circ\text{C}$  dan potential  $-0.4\text{V}$  vs  $\text{Ag}/\text{AgCl}$ . Homostruktur  $\text{Cu}_2\text{O}$  jenis p telah berjaya difabrikasi dan boleh dilaksanakan dalam homosimpang  $\text{Cu}_2\text{O}$  fotovolt untuk aplikasi sel solar.

## CONTENTS

<b>TITLE DECLARATION</b>	<b>i ii</b>
<b>DEDICATION</b>	<b>iii</b>
<b>ACKNOWLEDGMENT</b>	<b>iv</b>
<b>ABSTRACT</b>	<b>v</b>
<b>ABSTRAK</b>	<b>vi</b>
<b>CONTENTS</b>	<b>vii</b>
<b>LIST OF TABLES</b>	<b>xii</b>
<b>LIST OF FIGURES</b>	<b>xiv</b>
<b>LIST OF SYMBOL AND ABBREVIATION</b>	<b>xviii</b>
<b>CHAPTER 1 INTRODUCTION</b>	<b>1</b>
1.1 Project overview	1
1.2 Problem statement	3
1.3 Research objectives	3
1.4 Scope and limitations	4
1.5 Thesis Layout	4
<b>CHAPTER 2 LITERATURE REVIEW</b>	<b>6</b>
2.1 Copper oxide (Cu <sub>2</sub> O)	6

2.2 P-n homojunction thin film	7
2.3 Copper oxide homostructure thin film	9
2.4 Copper oxide fabrication	9
2.4.1 Substrate preparation for copper oxide fabrication	10
2.4.2 Parameters affect copper oxide fabrication	10
2.5 Electrodeposition method	13
2.6 Cyclic voltammetry measurement (CV)	14
2.7 Photoelectrochemical (PEC)	17
2.8 Photovoltaic (PV) and solar cell application	20
2.9 Summary	21
<b>CHAPTER 3 METHODOLOGY</b>	<b>23</b>
3.1 Fabrication process of homostructure thin film	23
3.1.1 Solution preparation	25
3.1.2 Substrate preparation	26
3.1.3 Electrodeposition process	28
3.1.4 Cyclic voltammetry (CV)	29
3.1.5 Photoelectrochemical (PEC) measurement	29
3.2 Characterization of thin film	30
3.2.1 Field Emission Scanning Electron Microscopy (FE-SEM)	30
3.2.2 X Ray Diffraction (XRD)	33
3.2.3 Surface Profiler	34



3.2.4	Ultraviolet-Visible Absorption Spectroscopy (UV-Vis)	35
3.2.5	Atomic Force Microscopy (AFM)	37
3.3	Summary	38
<b>CHAPTER 4</b>	<b>RESULTS AND ANALYSIS</b>	<b>40</b>
4.1	Fabrication of n-type $\text{Cu}_2\text{O}$ thin film on FTO substrate	40
4.1.1	Optimization of pH value for n-type $\text{Cu}_2\text{O}$ thin film fabrication	40
4.1.1.1	Structural properties	41
4.1.1.2	Morphological properties	43
4.1.1.3	Topological properties	45
4.1.1.4	Thickness analysis	46
4.1.1.5	Summary on pH value optimization for n-type $\text{Cu}_2\text{O}$ thin film	47
4.1.2	Optimization of deposition time for n-type $\text{Cu}_2\text{O}$ thin film fabrication	47
4.1.2.1	Structural properties	48
4.1.2.2	Morphological properties	49
4.1.2.3	Topological properties	51
4.1.2.4	Thickness analysis	52
4.1.2.5	Summary on pH value optimization for n-type $\text{Cu}_2\text{O}$ thin film	53
4.1.3	Optical properties and band gap	53
4.1.4	Cross-section of n-type $\text{Cu}_2\text{O}$ on FTO substrate	55



PTTA UTHM  
PERPUSTAKAAN TUNJUKKAN AMINAH



4.1.5 Photoelectrochemical (PEC) for n-type and p-type Cu <sub>2</sub> O thin film on FTO substrate	56
4.2 Fabrication of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	58
4.2.1 Cyclic voltammetry measurement for p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	59
4.2.2 Optimization of bath temperature for fabrication of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	61
4.2.2.1 Structural properties	62
4.2.2.2 Morphological properties	63
4.2.2.3 Summary on bath temperature for fabrication of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	64
4.2.3 Optimization of deposition time for fabrication of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	65
4.2.3.1 Structural properties	65
4.2.3.2 Morphological properties	67
4.2.3.3 Optical properties	68
4.2.3.4 Summary of deposition time for fabrication of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	70
4.2.4 Cross sectional of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	70
4.2.5 Photoelectrochemical (PEC) for p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	71
4.3 Summary	72



<b>CHAPTER 5 CONCLUSION AND FUTURE WORKS</b>	<b>74</b>
5.1 Conclusion and recommendations	74
<b>REFERENCES</b>	<b>77</b>
<b>APPENDIX</b>	<b>83</b>
<b>LIST OF PUBLICATIONS</b>	<b>84</b>
<b>VITAE</b>	<b>85</b>



**PTTA UTHM**  
PERPUSTAKAAN TUNKU TUN AMINAH

## LIST OF TABLES

2.1	Comparison between ITO and FTO substrate	10
2.2	Summary of parameters affect fabrication of n-type and p-type $\text{Cu}_2\text{O}$ thin films	12
2.3	Summary on subtopics in literature review	22
4.1	Different pH value used for n-type $\text{Cu}_2\text{O}$ thin film fabrication	40
4.2	Full width at Half Maximum of n-type $\text{Cu}_2\text{O}$ thin film deposition at pH value of 6.0, 6.3 and 6.5	42
4.3	The roughness of n-type $\text{Cu}_2\text{O}$ thin films corresponding pH value of sample	45
4.4	Different thickness of n-type $\text{Cu}_2\text{O}$ thin film obtained at different parameter of pH value	47
4.5	Different deposition time used for n-type $\text{Cu}_2\text{O}$ thin film fabrication	48
4.6	Full Width at half Maximum of n-type $\text{Cu}_2\text{O}$ thin films deposited at 20, 30, and 40 minutes	49
4.7	The roughness of n-type $\text{Cu}_2\text{O}$ thin films corresponding deposition time of sample	52
4.8	Different thickness of n-type $\text{Cu}_2\text{O}$ thin film obtained at different deposition time	53
4.9	Different deposition temperature for p-type $\text{Cu}_2\text{O}$ on n-type $\text{Cu}_2\text{O}$ /FTO substrate fabrication	61
4.10	Full Width at Half Maximum of n-type and p-type $\text{Cu}_2\text{O}$ deposited on n-type $\text{Cu}_2\text{O}$ /FTO substrate at different temperature	63
4.11	Different deposition time used for p-type $\text{Cu}_2\text{O}$ on n-type $\text{Cu}_2\text{O}$ /FTO substrate fabrication	65

4.12	Optimized parameters for n-type and p-type Cu <sub>2</sub> O thin film fabrication	73
------	------------------------------------------------------------------------------------	----



PTTA UTHM  
PERPUSTAKAAN TUNKU TUN AMINAH

## LIST OF FIGURES

2.1	Illustration of electrodeposition system	14
2.2	The voltammogram for solution at pH value of 7.0 and below	16
2.3	The voltammogram for solution at pH value of 9.0 and above	16
2.4	Illustration of photoelectrochemical measurement set up	18
2.5	Photo-voltage responses measured as a function of time pulse irradiation for n-type sample	18
2.6	Photo-voltage responses measured as a function of time pulse irradiation for p-type sample	19
2.7	Photocurrent responses from Cu <sub>2</sub> O electrodeposited at pH 11 and pH 7.5	19
2.8	Illustration of photovoltaic cell	20
3.1	Flowchart for fabrication of Cu <sub>2</sub> O based homojunction thin film	24
3.2	Illustration of fabrication layer for (a) n-type Cu <sub>2</sub> O thin film on FTO substrate and (b) p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate	25
3.3	Chemicals used to prepare copper acetate based solution (a) Copper (II) acetate monohydrate, (b) Lactic acid, (c) Pottasium hydroxide	25
3.4	Process of solution preparation (a) Chemicals were measured by using analytical balance measurement, (b) KOH was added until required pH value reached at 25°C, (c) The solution was kept for a day for stabilization	26
3.5	FTO glass substrate dimension of 2.5 cm x 1.5 cm	26
3.6	Dimension of deposition area is 1cm x 1cm	27
3.7	Polarization process of FTO glass substrate	28
3.8	Electrodeposition set up for fabrication of Cu <sub>2</sub> O thin film	29

3.9	PEC measurement set up for fabricated $\text{Cu}_2\text{O}$ thin film	30
3.10	Field Emission Scanning Electron Microscopy (FE-SEM) located at MiNT-SRC, UTHM	31
3.11	Illustration of sample stage for FE-SEM observation	32
3.12	The control panel of (a) sample stage and (b) operation stage, respectively	33
3.13	X-Ray Diffraction (XRD) Spectroscopy located at MiNT- SRC, UTHM	34
3.14	Surface profiler located at MiNT-SRC, UTHM	35
3.15	Illustration of thickness measurement concept by using Surface Profiler	35
3.16	UV-Vis Absorption Spectroscopy located at MiNT- SRC, UTHM	36
3.17	(a) Sample compartment and (b) illustration operation of UV- Vis Absorption Spectroscopy	37
3.18	Atomic Force Microscopy located at MiNT-SRC, UTHM	38
4.1	XRD pattern for (a) FTO coated glass substrate and n-type $\text{Cu}_2\text{O}$ thin films deposited at pH value of (b) 6.0, (c) 6.3 and (d) 6.5, respectively	42
4.2	FE-SEM morphological image for sample at pH 6.0 for magnification (a) 5,000x and (b) 1,000x	44
4.3	FE-SEM morphological image for sample at pH 6.3 for magnification (a) 5,000x and (b) 1,000x	44
4.4	FE-SEM morphological image for sample at pH 6.5 for magnification (a) 5,000x and (b) 1,000x	44
4.5	Topological images for n-type $\text{Cu}_2\text{O}$ thin film for sample deposited with (a) pH 6.0, (b) pH 6.3 and (c) pH 6.5, respectively	46
4.6	XRD pattern for (a) FTO and deposition n-type $\text{Cu}_2\text{O}$ thin films at (b) 20, (c) 30, and (d) 40 minutes	49
4.7	FE-SEM morphological image for sample deposited for 20 minutes for magnification (a) 5,000x and (b) 1,000x	50



4.8	FE-SEM morphological image for sample deposited for 30 minutes for magnification (a) 5,000x and (b) 1,000x	50
4.9	FE-SEM morphological image for sample deposited for 40 minutes for magnification (a) 5,000x and (b) 1,000x	51
4.10	AFM images for n-type Cu <sub>2</sub> O thin film for sample deposited for (a) 20, (b) 30, and (c) 40 minutes, respectively	52
4.11	Absorbance spectrum deposited n-type Cu <sub>2</sub> O using pH value 6.3 at 30 minutes	54
4.12	The extrapolated band gap for deposited n-type Cu <sub>2</sub> O using pH value 6.3 at 30 minutes	55
4.13	Cross sectional images of n-type Cu <sub>2</sub> O on FTO substrate at magnification of (a) 10,000x and (b) 5,000x	55
4.14	Photovoltage for Cu <sub>2</sub> O thin film sample at pH value of 6.3	57
4.15	Photovoltage for Cu <sub>2</sub> O thin film sample at pH value of 12.5	57
4.16	Energy band edge bending diagrams of (a) n-type and (b) p-type of Cu <sub>2</sub> O thin film/electrolyte system	58
4.17	Cyclic voltammetry for deposition of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate at 40°C. Region 1 and region 2 indicate the first and second reduction, respectively	60
4.18	Cyclic voltammetry of desposition of p-type Cu <sub>2</sub> O on n-type Cu <sub>2</sub> O/FTO substrate at 50°C. Region 1 and region 2 indicate the first and second reduction, respectively	60
4.19	XRD pattern for (a) FTO, (b) n-type Cu <sub>2</sub> O thin film on FTO substrate and p-type Cu <sub>2</sub> O deposited on n-type Cu <sub>2</sub> O/FTO substrate at (c) 40, (d) 50°C, respectively	62
4.20	The FE-SEM morphological images for (a) n-type Cu <sub>2</sub> O before deposition of p-type Cu <sub>2</sub> O thin film and after deposition of p-type Cu <sub>2</sub> O at (b) 40 and (c) 50°C, respectively	64
4.21	XRD pattern for (a) FTO; (b) n-type Cu <sub>2</sub> O before deposition of p type Cu <sub>2</sub> O thin film and after deposition of p-type Cu <sub>2</sub> O thin films for (c) 1 hour and (d) 2 hours, respectively	66



4.22	FE-SEM morphological images for (a) n-type $\text{Cu}_2\text{O}$ before deposition of p-type $\text{Cu}_2\text{O}$ thin film and after deposition of p-type $\text{Cu}_2\text{O}$ for (b) 1 hour and (c) 2 hours respectively	67
4.23	Absorbance spectrum for (a) n-type $\text{Cu}_2\text{O}$ before deposition of p-type $\text{Cu}_2\text{O}$ thin film and after deposition of p-type $\text{Cu}_2\text{O}$ for (b) 1 hour and (c) 2 hours, respectively	69
4.24	The extrapolated bandgap for deposited p-type $\text{Cu}_2\text{O}$ based homostructure using pH value 12.5 for 2 hours	69
4.25	Cross section images of p-type $\text{Cu}_2\text{O}$ on n-type $\text{Cu}_2\text{O}/\text{FTO}$ substrate at magnification of (a) 10,000x and (b) 5,000x	71
4.26	Photovoltage pattern $\text{Cu}_2\text{O}$ based homostructure thin film	72





## LISTS OF SYMBOLS AND ABBREVIATIONS

%	- Percentage
°	- Degree
μm	- micrometer
A	- Absorbance
a.u	- Absorbance unit
Ag/AgCl	- Silver/Silver Chloride
Al	- Aluminium
C	- Columb
CE	- Counter electrode
cm	- Centimeter
CO <sub>2</sub>	- Carbon Dioxide
Cu	- Copper
Cu <sub>2</sub> O	- Copper Oxide
CuSO <sub>4</sub>	- Copper Sulphate Pentahydrate
CV	- Cyclic Voltammetry
e	- Electron
ECL	- Electrochemiluminescence
E <sub>g</sub>	- Band gap
Fe <sub>2</sub> O <sub>3</sub>	- Iron Oxide
FE-SEM	- Field Emission-Scanning Electron Microscopy
FF	- Fill factor
FTO	- Fluorine doped tin oxide
h	- Plank's constant
H <sub>2</sub> O	- Water
ITO	- Indium tin oxide
I-V	- Current-voltage

$J_{sc}$	- Short Circuit Current
k	- kilo
KOH	- Potassium Hydroxide
M	- Mol
mA	- miliAmpere
MiNT-SRC	- Microelectronic and Nanotechnology Shamsuddin Research Centre
mV	- milivolt
MW	- Megawatt
NaCl	- Sodium Chloride
NaOH	- Sodium hydroxide
nm	- Nanometer
OCP	- Open circuit potential
$^{\circ}\text{C}$	- Degree Celsius
PEC	- Photoelectrochemical
ppm	- Parts per million
Pt	- Platinum
Pt	- Platinum
PV	- Photovoltaic
RE	- Reference electrode
RF	- Radio frequency
SCE	- Saturated calomel electrode
TCOs	- Transparent Conducting Oxide
$\text{TiO}_2$	- Titanium Dioxide
UV	- Ultraviolet
UV-Vis	- Ultraviolet-Visible Absorption Spectroscopy
V	- Volt
V/sec	- Volt per second
$V_{oc}$	- Open Circuit Voltage
vs	- Versus
WE	- Working electrode
XRD	- X-Ray Diffraction
ZnO	- Zinc Oxide

$a$	Alpha
$e$	Theta
$Q$	Olnn



## CHAPTER 1

### INTRODUCTION

This chapter discussed on the introduction of the project. This section consists of project overview, problem statement, research objectives, scopes and limitations of the project.

#### 1.1 Project overview

Nowadays, the population of the world seem grow rapidly and varies of industries had demand an energy which renewable for consumer. The renewable energy sources are including wind, hydro, solar, geothermal, and some producer of biomass. Based on International Energy Agency (IEA)'s statistic in 2012, the world trusted on renewable sources for around 13.2% of its total main energy supply. At 2013, renewables accounted for 22% of global electricity generation, which is a 5% increase from 2012 [1] .

Fossil fuel is the primary renewable source of energy among others. However, it is facing several challenges including high prices and pollution's effect by carbon dioxide emission. Carbon dioxide ( $\text{CO}_2$ ) is one type of gases which rises global temperature that cause climate change. Based on the increment rate of fossil fuel consumption, the concentration of  $\text{CO}_2$  is predicted to reach the dangerous level of 750 ppm in 2050. Since there is no natural decomposition of  $\text{CO}_2$  in the atmosphere, the pollution effect will take 500 to 2000 years to reduce [2]. Thus, finding new alternative on renewable energy source has received attention by consumers to

decrease CO<sub>2</sub> emission as alternative energy sources and invention for new technologies.

Solar energy is one of renewable energy through natural processes which use sun as the main source. It is consumable resource which provides more energy in one hour than the entire energy consumed by human in a whole year [2]. Hence, the photovoltaic industry, which is the direct conversion of solar energy to electricity, grew at a rate exceeding 30% per year in the last decade. The efficiency of solar-to-electron conversion is very important in the development of photovoltaic solar cells [4, 5].

Currently, wafer silicon acts as photovoltaic material for most industries. In 2009, solar cells based on large-grain polycrystalline and single-crystal silicon wafers include more than 80% of the photovoltaic market. However, the potential for price reduction is restricted by the bulk silicon wafer's cost. The high cost of these modules are caused by the processing and material cost. As a result, the electrical power production cost by solar energy higher than product by combustion of fossil fuels [4, 6].

Fabrication of thin film solar cell is one of major strategy to overcome the cost of electricity produced by photovoltaic modules. Thin film solar cells are known as the second generation photovoltaic devices which rapidly growing method in the photovoltaic technology. Thin film solar cells based on amorphous, microcrystalline, and polycrystalline silicon compound semiconductors have ascertained their commercial viability. Their market share increased steadily to 15% in 2009. In addition, by increase the efficiency beyond the Shockley–Queisser limit, it can reduce the cost of photovoltaic electricity. A variety of models are proposed along this venue to achieve high efficiency multi-junction solar cell based on III-V binary semiconductor. Initially, they are used in space application but now it is being developed for terrestrial application.

In this development, researchers found that p-n junction semiconductor is essential as a base for solid-state electronic devices including solar cell [6]. This concept was developed since study on movement of charge carriers in photovoltaic process was introduced. It was including both electron and hole formed a junction either in the same material which called homojunction or different materials known as heterojunction [7].

## 1.2 Problem statement

Nowadays, one of invention method for solar cell application is focusing on heterojunction energy conversion efficiency of copper oxide ( $\text{Cu}_2\text{O}$ ) solar cell to improve the efficiency conversion energy. However, there was low efficiency of solar cell based on the interface in heterojunction between p-type  $\text{Cu}_2\text{O}$  when other material create a loss mechanism for photo-carrier separation and collection [8]. In other research, the defects also most probably exist on the silicon interface in heterojunction especially order defect compound layer during deposition. So, it may affect the performance of the solar cells [9]. Therefore, another approach was introduced to improve the efficiency conversion such as p-n homojunction of  $\text{Cu}_2\text{O}$  solar cells. By using electrodeposition method with optimum parameters, it was reported that pH solution is one of the parameter that could control the total of oxygen into the growth of  $\text{Cu}_2\text{O}$  thin film [8]. Thus, the significant approach to increase efficiency in  $\text{Cu}_2\text{O}$  solar cells is to produce a homojunction of  $\text{Cu}_2\text{O}$  by optimizing the parameter such as pH value, deposition time and bath temperature using electrodeposition techniques. Thus, this research was purposed to fabricate n-type and p-type  $\text{Cu}_2\text{O}$  homostructure thin film by obtaining the optimum deposition parameters. The characterizations of  $\text{Cu}_2\text{O}$  homostructure also were carried out to enhance the performance of thin film's properties.

## 1.3 Research objectives

This research will be carried out in order to the following objectives:

1. To fabricate n-type  $\text{Cu}_2\text{O}$  thin film on FTO substrate and p-type  $\text{Cu}_2\text{O}$  on n-type  $\text{Cu}_2\text{O}$ /FTO substrate.
2. To optimize parameters such as pH value, deposition time and bath temperature for fabrication of n-type  $\text{Cu}_2\text{O}$  thin film on FTO substrate and p-type  $\text{Cu}_2\text{O}$  on n-type  $\text{Cu}_2\text{O}$ /FTO substrate.
3. To investigate the structural, morphological, topological and optical properties for both n-type  $\text{Cu}_2\text{O}$  and p-type  $\text{Cu}_2\text{O}$  based homostructure thin film.

## 1.4 Scope and limitation

The scopes of this project are as follow:

1. Copper (II) acetate monohydrate was used in this experiment as the based solution in electrodeposition method.
2. Deposition process were carried out using three electrodes set up which fluorine doped thin oxide (FTO) glass substrate as a working element, platinum (Pt) as a counter element and silver/silver chloride (Ag/AgCl) as a reference element.
3. The parameters of various pH value from 6.0 to 6.5 and deposition time between 20 and 40 minutes were conducted to optimize the performance of n-type  $\text{Cu}_2\text{O}$  thin film.
4. Cyclic voltammetry measurement of p-type  $\text{Cu}_2\text{O}$  thin film was carried out by using the same setting of three electrode set up as electrodeposition method.
5. Several parameters including bath temperature at 40 and 50 °C and deposition time for 1 hour and 2 hours were used to obtain the optimized p-type  $\text{Cu}_2\text{O}$  based homostructure thin film.
6. The characterization tools used were Field Emission Scanning Electron Microscopy (FE-SEM), X Ray Diffraction (XRD), Surface Profiler, Ultraviolet-Visible Absorption Spectroscopy (UV-Vis) and Atomic Force Microscopy (AFM).

## 1.5 Thesis layout

This thesis was discussed on fabrication of  $\text{Cu}_2\text{O}$  based homostructure thin films using electrodeposition method. The homostructure was constituted by two deposition layers which n-type and p-type  $\text{Cu}_2\text{O}$  thin films. Based on the objectives and scopes of project, there were five main chapters which explaining whole fabrication process.

In chapter 1, some introduction was briefing about project overview, problem statement, research objectives and scope. Several literature reviews were devoted in related subtopic such as copper oxide fabrication, homostructure, cyclic measurement, photoelectrochemical and photovoltaic concept. In addition, chapter 3

presented fabrication of  $\text{Cu}_2\text{O}$  thin films flowchart which including solution and substrate preparation, electrodeposition process and characterization properties. After that, chapter 4 showed the final results and discussion on structural, morphological, topological and optical properties for performances both n-type  $\text{Cu}_2\text{O}$  and p-type  $\text{Cu}_2\text{O}$  based homostructure thin film. Finally, conclusion was made up and recommendations for future works in this research was provided in chapter 5.



PTTA UTHM  
PERPUSTAKAAN TUNKU TUN AMINAH



## REFERENCES

- [1] P.Simon, "Renewable energy medium-term market report 2015. Market Analysis and Forecasts to 2020 - Executive Summary," *International Energy Agency (IEA)*, p. 14, 2015.
- [2] S. Lewis and G. Nocera, "Powering the planet : Chemical challenges in solar energy utilization," *PNAS*, vol. 103, no. 43, 2006.
- [3] V. Avrutin, N. Izyumskaya, and H. Morkoç, "Semiconductor solar cells: Recent progress in terrestrial applications," *Superlattices Microstruct.*, vol. 49, no. 4, pp. 337–364, Apr. 2011.
- [4] Y. Hsu, J. Wu, M. Chen, Y. Chen, and Y. Lin, "Fabrication of homojunction Cu<sub>2</sub>O solar cells by electrochemical deposition," *Appl. Surf. Sci.*, vol. 354, pp. 8–13, 2015.
- [5] F. Arith, S. A. M. Anis, M. M. Said, and C. M. I. Idris, "Low Cost Electro-deposition of Cuprous Oxide P-N Homo-junction Solar Cell," *Adv. Mater. Res.*, vol. 827, pp. 38–43, 2014.
- [6] S. V. Litvinenko, A. V. Kozinetz, and V. A. Skryshevsky, "Concept of photovoltaic transducer on a base of modified p-n junction solar cell," *Sensors Actuators A Phys.*, vol. 224, pp. 30–35, Apr. 2015.
- [7] M. Y. Abdu, "Copper (I) Oxide (Cu<sub>2</sub>O) Based Solar Cells - A Review," *Bayero J. Pure Appl. Sci.*, vol. 2, no. 2, pp. 8–12, 2009.
- [8] M. T. L. Wang, K. Han, X. Han, "P-n junction from solution: Cuprous oxide p-n homojunction by electrodeposition," in *33rd IEEE Photovoltaic Specialists Conference, PVSC '08.*, 2008, pp. 1–6.
- [9] J. Wu, X. Wang, and L. Zhang, "Interface Limits to Solar Efficiency in Chalcopyrite (p)/ Silicon (n) Hetero-junction Solar Cells," *2013 IEEE 39th Photovolt. Spec. Conf.*, pp. 1092–1097, 2013.
- [10] A. Maren and A. Fyhn, "Electrodeposition of Metal Oxides for Solar Cell Applications," 2012.

- [11] R. V. Alberto Mittiga, Enrico Salza, Francesca Sarto, Mario Tucci, "Heterojunction solar cell with 2 % efficiency based on a Cu<sub>2</sub>O substrate," *Appl. Phys. Lett.*, vol. 88, pp. 25–27, 2006.
- [12] J. K. D. S. J. K.M.D.C. Jayathilekea, W. Siripala, "Electrodeposition of p-type , n-type and p-n Homojunction Cuprous Oxide Thin Films," *Sri Lanka J. Phys.*, vol. 9, pp. 35–46, 2008.
- [13] A. Abdelfatah Mahmoud, Ledig Johannes, El-Shaer, Abdelhamid Wagner, Alexander Sharafeev, Azat Lemmens, Peter Mosaad, Mohsen Mohamed, Waag, Andreas Bakin, "Fabrication and characterization of flexible solar cell from electrodeposited Cu<sub>2</sub>O thin film on plastic substrate," *Sol. Energy*, vol. 122, pp. 1193–1198, 2015.
- [14] T. Mahalingam, J. S. P. Chitra, S. Rajendran, M. Jayachandran, and M. J. Chockalingam, "Galvanostatic deposition and characterization of cuprous oxide thin " lms," vol. 216, pp. 304–310, 2000.
- [15] A. R. Abdelwahed, "Potentiostatic Deposition and Characterization of Cuprous Oxide Thin Films," *Hindawi Publ. Corp.*, vol. 2013, pp. 1–5, 2013.
- [16] S. K. B. B.G. Streetman, *Solid State Electronic Devices 6th ed. Pearson int. ed.* 2010.
- [17] P. Bhattacharya, *Semiconductor Optoelectronic Devices 2nd ed.* 1997.
- [18] M. Tao, Longcheng Wang, "Fabrication and Characterization of p-n Homojunctions in Cuprous Oxide by Electrochemical Deposition," *Electrochem. Solid-State*, vol. 10, no. 9, pp. 248–250, 2007.
- [19] L. Yu, L. Xiong, and Y. Yu, "Cu<sub>2</sub>O Homojunction Solar Cells: F-Doped N-type Thin Film and Highly Improved Efficiency," *J. Phys. Chem. C*, vol. 119, no. 40, pp. 22803–22811, 2015.
- [20] A.-J. M. Chen Le, Shet Sudhakar, Tang Houwen, Wang Heli, Deutsch Todd, Yan Yanfa, Turner John, "Electrochemical deposition of copper oxide nanowires for photoelectrochemical applications," *J. Mater. Chem.*, vol. 20, no. 33, pp. 6962–6967, 2010.
- [21] S. T. Wei-min, Chao, Wen-how, Lan, Shao-yi Lee, Yi-chun Chou, Chun-wei Tsai, Ming-chang Shih, Yi-da Wu, "Investigation into the influence of the CuInSe<sub>2</sub> device with ITO and FTO layer," in *17th Opto-Electronics and Communications Conference (OECC 2012)*, 2012, no. July, pp. 671–672.



- [22] M. T. Kunhee Han, "Electrochemically deposited p – n homojunction cuprous oxide solar cells," *Sol. Energy Mater. Sol. Cells*, vol. 93, pp. 153–157, 2009.
- [23] R. H. A. Cornellissen, "Preparation and characterization of p-n homojunction Cu<sub>2</sub>O nanowire solar cells," 2012.
- [24] A. Sadat, S. Rahman, A. Islam, and K. Shorowordi, "Electrodeposition and Characterization of Copper Oxide Thin Films for Solar Cell Applications," no. 2, pp. 18–24, 2015.
- [25] S. M. Shahrestani, "Electrodeposition Of Cuprous Oxide For Thin Film Solar Cell Applications," p. 142, 2013.
- [26] V. Georgieva and M. Ristov, "Electrodeposited cuprous oxide on indium tin oxide for solar applications," *Sol. Energy Mater. Sol. Cells*, vol. 73, pp. 67–73, 2002.
- [27] F. E. Pavan Michele, Rühle Sven, Ginsburg Adam, Keller David A., Barad Hannah-Noa, Sberna Paolo M., Nunes Daniela, Martins Rodrigo, Anderson Assaf Y., Zaban Arie, "TiO<sub>2</sub>/Cu<sub>2</sub>O all-oxide heterojunction solar cells produced by spray pyrolysis," *Sol. Energy Mater. Sol. Cells*, vol. 132, pp. 549–556, Jan. 2015.
- [28] S. L. Artak, Karapetyan, Reymers Anna, Giorgio Suzanne, Fauquet Carole and M. W. Nitsche Serge, Nersesyan Manuk, Gevorgyan Vladimir, "Cuprous oxide thin films prepared by thermal oxidation of copper layer. Morphological and optical properties," *J. Lumin.*, vol. 159, pp. 325–332, Mar. 2015.
- [29] T. J. Song Huaibing, Zhan Xiaojun, Li Dengbing, Zhou Ying, Yang Bo, Zeng Kai, Zhong Jie, Miao Xiangshui, "Rapid thermal evaporation of Bi<sub>2</sub>S<sub>3</sub> layer for thin film photovoltaics," *Sol. Energy Mater. Sol. Cells*, vol. 146, pp. 1–7, Mar. 2016.
- [30] J. F. Wang Y., Ghanbaja, J., Soldera F., Migot S., Boulet P., Horwat D., Mücklich F., Pierson, "Tuning the structure and preferred orientation in reactively sputtered copper oxide thin films," *Appl. Surf. Sci.*, vol. 335, pp. 85–91, Apr. 2015.
- [31] A. J. B. L. R. Faulkner, *Electrochemical methods Fundamentals and Applications*. 2001.
- [32] H. Lee, J.-H. Lee, Y.-H. Hwang, and Y. Kim, "Cyclic voltammetry study of electrodeposition of CuGaSe<sub>2</sub> thin films on ITO-glass substrates," *Curr. Appl. Phys.*, vol. 14, no. 1, pp. 18–22, Jan. 2014.



PTIAUTHM  
PUSAT PENELITIAN DAN PENGEMBANGAN TEKNOLOGI DAN INOVASI

- [33] Y. S. Chaudhary, A. Agrawal, R. Shrivastav, V. R. Satsangi, and S. Dass, "A study on the photoelectrochemical properties of copper oxide thin films," *Int. J. Hydrogen Energy*, vol. 29, no. 2, pp. 131–134, 2004.
- [34] W. W. Qiu, Yanxia, Jing Li, Hongbo Li, Qi Zhao, Hongmei Wang, Hailin Fang, Dahe Fan, "A facile and ultrasensitive photoelectrochemical sensor for copper ions using in-situ electrodeposition of cuprous oxide," *Sensors Actuators, B Chem.*, vol. 208, pp. 485–490, 2015.
- [35] L. Xiong, S. Huang, X. Yang, M. Qiu, Z. Chen, and Y. Yu, "P-type and n-type Cu<sub>2</sub>O semiconductor thin films: Controllable preparation by simple solvothermal method and photoelectrochemical properties," *Electrochim. Acta*, vol. 56, no. 6, pp. 2735–2739, 2011.
- [36] P. Würfel, "Physics of Solar Cells," *WILEY-VCH Verlag GmbH & Co. KGaA*, pp. 37–84, 2005.
- [37] B. Parida, S. Iniyar, and R. Goic, "A review of solar photovoltaic technologies," *Renew. Sustain. Energy Rev.*, vol. 15, no. 3, pp. 1625–1636, Apr. 2011.
- [38] H. Z. Å and Wei, "The history of solar," *Solar Energy Materials and Solar Cells*, vol. 93, pp. 1461–1470, 2011.
- [39] M. A. Shah, "Preparation of Copper (Cu) and Copper Oxide (Cu<sub>2</sub>O) Nanoparticles under Supercritical Conditions," *Mater. Sci. Appl.*, vol. 2, no. August, pp. 977–980, 2011.
- [40] Stern M.; Geary A. L., "Electrochemical Polarization : A Theoretical Analysis of the Shape of Polarization Curves," *J. Electrochem. Soc.*, vol. 104, no. 1, pp. 56–63, 1957.
- [41] Y. Tang, Z. Chen, Z. Jia, L. Zhang, and J. Li, "Electrodeposition and characterization of nanocrystalline cuprous oxide thin films on TiO<sub>2</sub> films," vol. 59, pp. 434–438, 2005.
- [42] V. D. Hodoroba, D. Akcakayiran, D. O. Grigoriev, and D. G. Shchukin, "Characterization of micro- and nanocapsules for self-healing anti-corrosion coatings by high-resolution SEM with coupled transmission mode and EDX," *Analyst*, vol. 139, no. 8, pp. 2004–2010, 2014.
- [43] B. D. Cullity, *Elements of X-ray diffraction*. 1978.



- [44] M. R. Amirzada, "Optimization in the Technological Steps for the Fabrication of Large Area Micromirror Arrays Optimization in the Technological Steps for the Fabrication of Large Area Micromirror Arrays," 2014.
- [45] P. P. G. R. Rutuja S Shah\*, Rutuja R Shah, Rajashri B Pawar, "UV-Visisble Spectroscopy-A Review," *Int. J. Institutional Pharm. Life Sci.*, vol. 5, no. August, pp. 131–150, 2015.
- [46] A. Sasha and R. Zafiruddin, "Cyclic Voltammetry Measurement For N-type Cu<sub>2</sub>O Thin Film Using Copper Acatate-Based Solution," *ARPN J. Eng. Appl. Sci.*, vol. 10, no. 19, pp. 6–11, 2015.
- [47] M. N. N. and M. A. A. R.-A. V A Gevorkyan, A E Reymers, "Characterization of Cu<sub>2</sub>O thin films prepared by evaporation of CuO powder," in *Journal of Physics: Conference Series*, 2015, vol. 12027, pp. 1–7.
- [48] B. B. M. El Hajji, A. Hallaoui, L. Bazzi, A. Benlhachemi, O. Jbara, A.Tara, "Nanostructured ZnO, ZnO-CeO<sub>2</sub>, ZnO-Cu<sub>2</sub>O thin films electrodes prepared by electrodeposition for electrochemical degradation of dye," *Int. J. Electrochem. Sci.*, vol. 9, pp. 4297–4314, 2014.
- [49] S. J. Nurani, M. A. Islam, A. S. M. S. Rahman, M. G. Mowla, and K. M. Shorowordi, "Electrodeposition and dependency of optical properties on operating voltage and bath temperature of Copper oxide (II) thin films for photovoltaic applications," in *2015 IEEE International Conference on Telecommunications and Photonics (ICTP)*, 2015, pp. 1–5.
- [50] Y. Hwang, H. Ahn, M. Kang, and Y. Um, "The effects of thermally-induced biaxial stress on the structural , electrical , and optical properties of Cu<sub>2</sub>O thin fi lms," *Curr. Appl. Phys.*, vol. 15, pp. S89–S94, 2015.
- [51] M. Voinea, C. Vladuta, C. Bogatu, and A. Duta, "Surface properties of copper based cermet materials," *Mater. Sci. Eng. B Solid-State Mater. Adv. Technol.*, vol. 152, no. 1–3, pp. 76–80, 2008.
- [52] K. Akimoto, S. Ishizuka, M. Yanagita, Y. Nawa, G. K. Paul, and T. Sakurai, "Thin film deposition of Cu<sub>2</sub>O and application for solar cells," *Sol. Energy*, vol. 80, pp. 715–722, 2006.
- [53] H. Hashemipour, M. E. Zadeh, and R. Pourakbari, "Investigation on synthesis and size control of copper nanoparticle via electrochemical and chemical reduction method," *Int. J. Phys. Sci. Vol.*, vol. 6, no. 18, pp. 4331–4336, 2011.



- [54] V. Dhanasekaran, T. Mahalingam, R. Chandramohan, J.-K. Rhee, and J. P. Chu, "Electrochemical deposition and characterization of cupric oxide thin films," *Thin Solid Films*, vol. 520, no. 21, pp. 6608–6613, 2012.
- [55] A. S. M. S. Rahman, M. A. Islam, and K. M. Shorowordi, "Electrodeposition and Characterization of Copper Oxide Thin Films for Solar cell Applications," *Procedia Eng.*, vol. 105, no. 1, pp. 679–685, 2014.
- [56] J. S. a Masanobu Izaki, Shunsuke Sasaki, Fariza Binti Mohamad, Tsutomu Shinagawa, Takayuki Ohta, Seiji Watase, "Effects of preparation temperature on optical and electrical characteristics of (111)-oriented  $\text{Cu}_2\text{O}$  films electrodeposited on (111)-Au film," *Thin Solid Films*, vol. 520, no. 6, pp. 1779–1783, 2012.
- [57] V. Kumar, S. Masudi-Panah, C. C. Tan, T. K. S. Wong, D. Z. Chi, and D. G. K., "Copper Oxide Based Low Cost Thin Film Solar Cells," *IEEE 5th Int. Nanoelectron. Conf.*, pp. 443–445, 2013.



PTTA UTHM  
PERPUSTAKAAN TUNKU TUN AMINAH